



Item #151641

3.5 Techniflex White Polyolefin / AP151 Opaque @ 1.70 Cwt. /

FACESTOCK

3.5 Techniflex White Polyolefin

A 3.5 mil white polyolefin label film for pressure sensitive applications that offers excellent moisture resistance, stain resistance, dimensional stability and squeezability.

Type: Film

Caliper: 3.50 Mil

Opacity: 85.0

Brightness: N/A

Basis Weight: N/A

Tensile: MD: 34000 Psi, CD: 18000 Psi

Tear: MD: 37 Grams, CD: N/A

Elongation: MD: 500, CD: 40

REGULATORY APPROVAL

RoHS: Yes

REACH: Yes

CPSIA: Yes

Prop 65: Yes

TPCH: Yes

Indirect Food: Yes

Direct Food: Yes

UL:

ADHESIVE

AP151 Opaque @ 1.70 Cwt.

An outstanding general purpose permanent opaque adhesive that has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting and stripping traits. Provides opacity for cover up applications.

Adhesive Type: Permanent Latex

Shear: 80 min.

Minimum Application Temperature: 35 F

Service Temperature: 65- F to 220 F

TYPICAL ADHESION VALUES

Stainless Steel: 180° Peel: 7.3 lb/in,

Loop Tack: 5.00 lb/in²

Glass: 180° Peel: 5.7 lb/in

Polyethylene: 180° Peel: 6.5 lb/in

Corrugated: 180° Peel: 7.3 lb/in

Painted Metal: 180° Peel: 7.5 lb/in

REGULATORY APPROVAL

RoHS: Yes

REACH: Yes

CPSIA: Yes

Prop 65: Yes

TPCH: Yes

Indirect Food: Yes

Direct Food: No

UL:

RELEASE LINER

Basis Weight: lb/ream

Tensile: MD: N/A lb/in, CD: N/A

Caliper: mil

Tear: MD: N/A, CD: N/A

REGULATORY APPROVAL

RoHS:

REACH:

CPSIA:

Prop 65:

TPCH:

Indirect Food:

Direct Food:

UL:

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE'S standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

TECHNICOTE CORPORATE HEADQUARTERS 222 Mound Avenue Miamisburg, OH 45342 800-358-4448 technicote.com