©©Technicote[®]

Item #4402275

50# BW EDP / TS523 @ 1.50 Cwt. / 65# FBK L-3

FACESTOCK 50# BW EDP

This is a high brightness, surface-sized free sheet. Its smoothness and optical properties are designed to yield clean, crisp printed images. Its physical properties provide the dimensional stability and strength required in the pressure sensitive label converting process.

Type: Paper Caliper: 3.50 Mil Opacity: 90.0 Brightness: 92 Basis Weight: 50lbs/3300 sq ft Tensile: MD: 30 Lbs/in, CD: 15 Lbs/in Tear: MD: 40 Grams, CD: 50 Grams Elongation: MD: N/A, CD: N/A

REGULATORY APPROVAL RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: No UL:

ADHESIVE TS523 @ 1.50 Cwt.

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Adhesive Type: Permanent Acrylic Shear: 350 min. Minimum Application Temperature: 35 F Service Temperature: -65 F to 200 F

TYPICAL ADHESION VALUES Stainless Steel: 180° Peel: 5.6 lb/in, Loop Tack: 2.70 lb/in² Glass: 180° Peel: 2.8 lb/in Polyethylene: 180° Peel: 2.9 lb/in Corrugated: 180° Peel: 4.0 lb/in Painted Metal: 180° Peel: 4.6 lb/in

REGULATORY APPROVAL RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: No UL:

RELEASE LINER 65# FBK L-3

A fully bleached kraft liner which has been silicone coated one side to give a controlled release. This paper has high internal strength to withstand all conventional processing operations including die-cutting, perforating, fanfolding and refolding processes.

Basis Weight: O lb/ream Tensile: MD: 33 lb/in, CD: 18 Caliper: 3.8 mil Tear: MD: N/A, CD: N/A

REGULATORY APPROVAL

RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Direct Food: UL:

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE's standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

TECHNICOTE CORPORATE HEADQUARTERS 222 Mound Avenue Miamisburg, OH 45342 800-358-4448 technicote.com