



Item #75753

2 mil Crystal Clear Polypropylene / TS585WS @ 1.60 Cwt. / 44# PK L-4

FACESTOCK

2 mil Crystal Clear
Polypropylene

A 2 mil clear biaxially oriented polypropylene with exceptional clarity, excellent die-cut performance and great stiffness. Coated gloss surface is print receptive for standard methods.

Type: Film

Caliper: 2.00 Mil

Opacity: N/A

Brightness: NA

Basis Weight: NA

Tensile: MD: 20,000 psi, CD: 35,000 psi

Tear: MD: NA, CD: NA

Elongation: MD: 180, CD: 55%

REGULATORY APPROVAL

RoHS: Yes

REACH: Yes

CPSIA: Yes

Prop 65: Yes

TPCH: Yes

Indirect Food: Yes

Direct Food: No

UL: No

ADHESIVE

TS585WS @ 1.60 Cwt.

A specialty adhesive designed to adhere to slightly wet surfaces with good ultimate adhesion when applied at temperatures as low as -20 F. Excellent permanency at room temperatures. Good plasticizer, UV & solvent resistance. Excellent adhesive for hard to label substrates.

Adhesive Type: Permanent Acrylic

Shear: 65 min.

Minimum Application Temperature: 20- F

Service Temperature: 65- F to 140 F

TYPICAL ADHESION VALUES

Stainless Steel: 180° Peel: 4.8 lb/in,

Loop Tack: 2.70 lb/in²

Glass: 180° Peel: 3.2 lb/in

Polyethylene: 180° Peel: 2.0 lb/in

Corrugated: 180° Peel: 3.3 lb/in

Painted Metal: 180° Peel: 4.1 lb/in

REGULATORY APPROVAL

RoHS: Yes

REACH: Yes

CPSIA: Yes

Prop 65: Yes

TPCH: Yes

Indirect Food: Yes

Direct Food: No

UL:

RELEASE LINER

44# PK L-4

A medium weight natural kraft coated 1 side (C1S) with a gloss polyethylene. Silicone coating has been added on the gloss side (C1S) for a controlled release. It has superb smoothness, excellent dimensional stability and exceptional layflat characteristics.

Basis Weight: 44 lb/ream

Tensile: MD: 0 lb/in, CD: 0

Caliper: 3.2 mil

Tear: MD: N/A, CD: N/A

REGULATORY APPROVAL

RoHS: Yes

REACH: Yes

CPSIA: Yes

Prop 65: Yes

TPCH: Yes

Indirect Food:

Direct Food:

UL:

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE'S standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

TECHNICOTE CORPORATE HEADQUARTERS 222 Mound Avenue Miamisburg, OH 45342 800-358-4448 technicote.com