

Item #77329

Techni-Therm (TM) III / GP550 向 1.30 Cwt. / 40# SCK L-3 TU

FACESTOCK

Techni-Therm (TM) III

A coated one side thermal transfer facestock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This facestock also offers a 90% brightness and an 82% opacity.

Type: Paper Caliper: 2.65 Mil Opacity: 82 Brightness: 90

Basis Weight: 44lbs/3300 sq ft Tensile: MD: 25 Lbs/in, CD: 16 Lbs/in Tear: MD: 34 Grams, CD: 36 Grams Elongation: MD: N/A, CD: N/A

REGULATORY APPROVAL

RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: No

UL: No

ADHESIVE GP550 向 1.30 Cwt.

A general purpose permanent acrylic with good initial tack and high ultimate adhesion. This adhesive is available on Thermal Transfer and Direct Thermal NTC paper face stocks, and displays excellent adhesion to most substrates where thermal transfer and non-topcoated direct thermal paper labels are typically utilized.

Adhesive Type: Permanent Acrylic

Shear: 100 min.

Minimum Application Temperature: 20- F **Service Temperature:** -65 F to 200 F

TYPICAL ADHESION VALUES **Stainless Steel:** 180° Peel: 4.8 lb/in,

Loop Tack: 2.90 lb/in² Glass: 180° Peel: 4.4 lb/in Polyethylene: 180° Peel: 3.9 lb/in Corrugated: 180° Peel: 3.0 lb/in Painted Metal: 180° Peel: 4.0 lb/in

REGULATORY APPROVAL

RoH5: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: No UL:

RELEASE LINER

40# SCK L-3 TU

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. Technicote Ultimate silicone release coating provides consistent stripping at high converting speeds through a flat release profile. This paper has a smooth, caliper consistent surface and withstands all conventional processing operations.

Basis Weight: 40 lb/ream Tensile: MD: 30 lb/in, CD: 20

Caliper: 2.5 mil Tear: MD: N/A, CD: N/A

REGULATORY APPROVAL

RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Direct Food: UL:

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE'S standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.