

Item #78924

Majestic White 230(TM) PP / IP400 @ 1.50 Cwt. / 44# PK L-4

FACESTOCK

Majestic White 230(TM) PP

A topcoated white polypropylene film with a gloss level of 48%. Product has excellent printability (Thermal Transfer printability with a resin ribbon only), temperature resistance & semi squeezable performance. This face offers balanced orientation for superior die cutting and high stiffness for conversion and automatic dispensing.

Type: Film Caliper: 2.30 Mil Opacity: 80.0 Brightness: N/A Basis Weight: N/A

Tensile: MD: 25400 Psi, CD: 22500 Psi

Tear: MD: N/A, CD: N/A **Elongation:** MD: 95, CD: 115

REGULATORY APPROVAL

RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: No

UL:

ADHESIVE

A specialty adhesive designed to adhere to glass wine bottles with good ultimate adhesion when applied at temperatures as low as +35 F. Excellent permanency at room temperatures. Good plasticizer, UV & solvent resistance. Excellent adhesive for wet strength wine label facestocks when submersed in ice buckets.

Adhesive Type: Permanent Acrylic

Shear: 80 min.

Minimum Application Temperature: 35 F **Service Temperature:** -65 F to 200 F

TYPICAL ADHESION VALUES **Stainless Steel:** 180° Peel: 5.5 lb/in,

Loop Tack: 5.00 lb/in² Glass: 180° Peel: 3.2 lb/in Polyethylene: 180° Peel: 2.0 lb/in Corrugated: 180° Peel: 3.3 lb/in Painted Metal: 180° Peel: 5.0 lb/in

REGULATORY APPROVAL

RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: No

UL:

RELEASE LINER

44# PK L-4

A medium weight natural kraft coated 1 side (C15) with a gloss polyethylene. Silicone coating has been added on the gloss side (C15) for a controlled release. It has superb smoothness, excellent dimensional stability and exceptional layflat characteristics.

Basis Weight: 44 lb/ream **Tensile:** MD: 0 lb/in, CD: 0 **Caliper:** 3.2 mil

Tear: MD: N/A, CD: N/A

REGULATORY APPROVAL

RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Direct Food: UL:

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE'S standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.