



Item #81029

2 mil Storm Clear / AT150 @ 1.30 Cwt. / 40#SCK L-3

FACESTOCK

2 mil Storm Clear

A high performance, 2 mil clear biaxially oriented polypropylene film. Corona treated for excellent label printing performance by a wide variety of print methods.

Type: Film

Caliper: 2.00 Mil

Opacity: N/A

Brightness: N/A

Basis Weight: N/A

Tensile: MD: 20590 Psi, CD: 39050 Psi

Tear: MD: N/A, CD: N/A

Elongation: MD: 210, CD: 75

REGULATORY APPROVAL

RoHS: Yes

REACH: Yes

CPSIA: Yes

Prop 65: Yes

TPCH: Yes

Indirect Food: Yes

Direct Food: Yes

UL:

ADHESIVE

AT150 @ 1.30 Cwt.

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 °F. Very good plasticizer, UV and solvent resistance. AT150 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps

Adhesive Type: Permanent Acrylic

Shear: 100 min.

Minimum Application Temperature: -20 °F

Service Temperature: -65 °F to 160 °F

TYPICAL ADHESION VALUES

Stainless Steel: 180° Peel: 5.1 lb/in,

Loop Tack: 2.90 lb/in²

Glass: 180° Peel: 4.4 lb/in

Polyethylene: 180° Peel: 4.2 lb/in

Corrugated: 180° Peel: 4.7 lb/in

Painted Metal: 180° Peel: 3.1 lb/in

REGULATORY APPROVAL

RoHS: Yes

REACH: Yes

CPSIA: Yes

Prop 65: No

TPCH: Yes

Indirect Food: Yes

Direct Food: No

UL: No

RELEASE LINER

40#SCK L-3

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Basis Weight: 0 lb/ream

Tensile: MD: 34 lb/in, CD: 22

Caliper: 2.5 mil

Tear: MD: N/A, CD: N/A

REGULATORY APPROVAL

RoHS: Yes

REACH: Yes

CPSIA: Yes

Prop 65: Yes

TPCH: Yes

Indirect Food:

Direct Food:

UL:

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE'S standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.