

Item #85780

Tyvek(R) 1073-D / TR440 @ 1.00 Cwt. / 3.4 Mil Layflat L-5

FACESTOCK

Tyvek(R) 1073-D

A durable sheet that is stronger than paper, less expensive and more versatile than fabrics. It is made from high density polyethylene fibers and is considered a spunbonded olefin offering a balance of physical characteristics likened to a paper, film and cloth.

Type: Film Caliper: 8.00 Mil Opacity: N/A Brightness: N/A Basis Weight: N/A

Tensile: MD: 42 Lbs/in, CD: 48 Lbs/in **Tear:** MD: 453 Grams, CD: 453 Grams

Elongation: MD: 20, CD: 24

REGULATORY APPROVAL

RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: No

UL:

ADHESIVE TR440 向 1.00 Cwt.

A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.

Adhesive Type: Removable Acrylic

Shear: 110 min.

Minimum Application Temperature: 40 F **Service Temperature:** 65- F to 150 F

TYPICAL ADHESION VALUES **Stainless Steel:** 180° Peel: 4.7 lb/in,

Loop Tack: 1.70 lb/in²
Glass: 180° Peel: 3.0 lb/in
Polyethylene: 180° Peel: 1.4 lb/in
Corrugated: 180° Peel: 3.2 lb/in
Painted Metal: 180° Peel: 4.5 lb/in

REGULATORY APPROVAL

RoH5: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: No

UL:

RELEASE LINER3.4 Mil Layflat L-5

A bleached kraft liner which has been silicone coated one side to give a controlled release. It is designed to withstand diecutting, marginal punching, perforating, fanfolding and refolding process while providing excellent dimensional stability.

Basis Weight: O lb/ream Tensile: MD: 35 lb/in, CD: 15

Caliper: 3.4 mil Tear: MD: N/A, CD: N/A

REGULATORY APPROVAL

RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: UL:

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE's standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.