

# Item #8810047

65# Premium Matte White Ink Jet / TS585WS/LPG a 1.60 Cwt. / 44# PK L-4

#### **FACESTOCK**

# 65# Premium Matte White Ink Jet

A premium matte-coated photo grade paper offering universal compatibility with a wide range of water based ink jet printing technologies. The paper offers instant-dry properties, outstanding contrasts, high resolution print performance and improved waterfastness vs. standard matte grades.

Type: Paper Caliper: 5.00 Mil Opacity: N/A Brightness: N/A Basis Weight: 65

Tensile: MD: N/A, CD: N/A
Tear: MD: N/A, CD: N/A
Elongation: MD: N/A, CD: N/A

## REGULATORY APPROVAL

RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: No

UL:

## **ADHESIVE**

## TS585WS/LPG a 1.60 Cwt.

A specialty adhesive designed to adhere to slightly wet surfaces with good ultimate adhesion when applied at temperature s as low as -20F. Excellent permanency at room temperatures. Good plasticizer, UV and solvent resistance. Excellent adhesive for hard to label substrates.

Adhesive Type: Permanent Acrylic

Shear: 65 min.

**Minimum Application Temperature**: 20- F **Service Temperature**: 65- F to 140 F

TYPICAL ADHESION VALUES Stainless Steel: 180° Peel: 4.8 lb/in,

Loop Tack: 2.70 lb/in<sup>2</sup> **Glass:** 180° Peel: 3.2 lb/in **Polyethylene:** 180° Peel: 2.0 lb/in **Corrugated:** 180° Peel: 3.3 lb/in **Painted Metal:** 180° Peel: 4.1 lb/in

#### REGULATORY APPROVAL

RoH5: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: No

UL:

### **RELEASE LINER**

44# PK L-4

A medium weight natural kraft coated 1 side (C15) with a gloss polyethylene. Silicone coating has been added on the gloss side (C15) for a controlled release. It has superb smoothness, excellent dimensional stability and exceptional layflat characteristics.

Basis Weight: 44 lb/ream Tensile: MD: 0 lb/in, CD: 0 Caliper: 3.2 mil Tear: MD: N/A, CD: N/A

REGULATORY APPROVAL

RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: UL:

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE'S standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.