



# Item #89032

/ TS523 @ 1.50 Cwt. / 1.5 mil Clear Polyester L-10

## RELEASE LINER

**Basis Weight:** lb/ream  
**Tensile:** MD: N/A lb/in, CD: N/A  
**Caliper:** mil  
**Tear:** MD: N/A, CD: N/A

### REGULATORY APPROVAL

**RoHS:**  
**REACH:**  
**CPSIA:**  
**Prop 65:**  
**TPCH:**  
**Indirect Food:**  
**Direct Food:**  
**UL:**

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE'S standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

**TECHNICOTE CORPORATE HEADQUARTERS** 222 Mound Avenue Miamisburg, OH 45342 800-358-4448 [technicote.com](http://technicote.com)

## ADHESIVE

TS523 @ 1.50 Cwt.

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

**Adhesive Type:** Permanent Acrylic

## RELEASE LINER

1.5 mil Clear Polyester L-10

A 1.5 mil polyester liner which has been silicone coated one side to give a controlled release. It has extremely high internal strength for ease in manufacturing, converting and end usage, making it an outstanding liner for high speed, automatic applications.

**Basis Weight:** 0 lb/ream

**Shear:** 350 min.  
**Minimum Application Temperature:** 35 F  
**Service Temperature:** -65 F to 200 F

**Tensile:** MD: 32000 lb/in, CD: 0  
**Caliper:** 1.5 mil  
**Tear:** MD: N/A, CD: N/A

#### TYPICAL ADHESION VALUES

**Stainless Steel:** 180° Peel: 5.6 lb/in,  
Loop Tack: 2.70 lb/in<sup>2</sup>  
**Glass:** 180° Peel: 2.8 lb/in  
**Polyethylene:** 180° Peel: 2.9 lb/in  
**Corrugated:** 180° Peel: 4.0 lb/in  
**Painted Metal:** 180° Peel: 4.6 lb/in

#### REGULATORY APPROVAL

**RoHS:** Yes  
**REACH:** Yes  
**CPSIA:** Yes  
**Prop 65:** Yes  
**TPCH:** Yes  
**Indirect Food:**  
**Direct Food:**  
**UL:**

#### REGULATORY APPROVAL

**RoHS:** Yes  
**REACH:** Yes  
**CPSIA:** Yes  
**Prop 65:** Yes  
**TPCH:** Yes  
**Indirect Food:** Yes  
**Direct Food:** No  
**UL:**

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE'S standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

**TECHNICOTE CORPORATE HEADQUARTERS** 222 Mound Avenue Miamisburg, OH 45342 800-358-4448 [technicote.com](http://technicote.com)