

# Not a Current Stock Product - Please contact Technical Services at 800-358-4448 for assistance.

60# C1S Matte Litho / Permanent / 4.6 mil Scoreback

#### **FACESTOCK**

### 60# C1S Matte Litho

A premium matte litho stock with excellent ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face comes with a brightness of 84% and an opacity of 93%.

Type: Paper Caliper: 3.90 Mil Opacity: 93.0 Brightness: 84

Basis Weight: 60lbs/3300 sq ft Tensile: MD: N/A, CD: N/A Tear: MD: 50 Grams, CD: 55 Grams Elongation: MD: N/A, CD: N/A

## REGULATORY APPROVAL

RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: No

UL:

# **ADHESIVE**

## Permanent

A general purpose acrylic adhesive showing good initial tack with high shear and ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Adhesive Type: Permanent Acrylic

Shear: 300 min

Minimum Application Temperature: 35°F Service Temperature: -65 to 180°F

TYPICAL ADHESION VALUES **Stainless Steel:** 180° Peel: 5.2 lb/in,

Loop Tack: 2.20 lb/in<sup>2</sup>
Glass: 180° Peel: 3.2 lb/in
Polyethylene: 180° Peel: 1.5 lb/in
Corrugated: 180° Peel: 3.4 lb/in
Painted Metal: 180° Peel: 4.5 lb/in

## REGULATORY APPROVAL

RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: Yes UL:

## **RELEASE LINER**

## 4.6 mil Scoreback

A bleached kraft which has been silicone coated one side to give a controlled release. This paper has high internal strength to withstand all conventional processing operations including die-cutting and butt-cutting. The back is scored for the purpose of bending, creasing, folding or tearing.

Basis Weight: 0 lb/ream Tensile: MD: 0 lb/in, CD: 0

Caliper: 4.6 mil Tear: MD: N/A, CD: N/A

#### REGULATORY APPROVAL

RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Direct Food:

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE's standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.