



Not a Current Stock Product - Please contact Technical Services at 800-358-4448 for assistance.

60# Matte Litho Opaque / PA26 / 4.6 mil Scoreback

FACESTOCK

60# Matte Litho Opaque

A premium matte litho stock with excellent ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This stock offers a gray back for added opacity

Type: Paper
Caliper: 3.9 mil
Opacity: >93
Brightness: 80
Basis Weight: 60 Lbs/3300 sq ft
Tensile: MD: N/A, CD: N/A
Tear: MD: 50 grams, CD: 55 grams
Elongation: MD: NA, CD: NA

REGULATORY APPROVAL

RoHS: Yes
REACH: Yes
CPSIA: Yes
Prop 65: Yes
TPCH: Yes
Indirect Food: Yes
Direct Food: Yes
UL: Yes

ADHESIVE

PA26

A general purpose hotmelt adhesive with high initial tack and excellent ultimate adhesion. This adhesive demonstrates good resistance to water, UV, solvent and plasticizer. PA26 has outstanding adhesion to most plastic substrates, especially HDPE, and many other plastics.

Adhesive Type: Permanent Hot Melt
Shear: 50 min.
Minimum Application Temperature: 25 F
Service Temperature: 65- F to 140 F

TYPICAL ADHESION VALUES

Stainless Steel: 180° Peel: 4.7 lb/in, Loop Tack: 2.50 lb/in²
Glass: 180° Peel: 4.0 lb/in
Polyethylene: 180° Peel: 5.6 lb/in
Corrugated: 180° Peel: 4.5 lb/in
Painted Metal: 180° Peel: 5.4 lb/in

REGULATORY APPROVAL

RoHS:
REACH:
CPSIA:
Prop 65:
TPCH:
Indirect Food: Yes
Direct Food: Yes
UL:

RELEASE LINER

4.6 mil Scoreback

A bleached kraft which has been silicone coated one side to give a controlled release. This paper has high internal strength to withstand all conventional processing operations including die-cutting and butt-cutting. The back is scored for the purpose of bending, creasing, folding or tearing.

Basis Weight: 0 lb/ream
Tensile: MD: 0 lb/in, CD: 0
Caliper: 4.6 mil
Tear: MD: N/A, CD: N/A

REGULATORY APPROVAL

RoHS: Yes
REACH: Yes
CPSIA: Yes
Prop 65: Yes
TPCH: Yes
Indirect Food:
Direct Food:
UL:

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE'S standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.