©©Technicote[®]

Item #20026

TF335 @ 1.50 Cwt.

ADHESIVE TF335 @ 1.50 Cwt.

A freezer grade rubber based adhesive with good initial tack and good ultimate adhesion when applied at temperatures as low as -20 F. This is a firm, minimal cold flow adhesive. A true freezer grade adhesive that is very permanent at cold temps, yet semiremovable at room temps.

Adhesive Type: Semi-Permanent Latex Shear: 50 min. Minimum Application Temperature: 20- F Service Temperature: 65- F to 140 F

TYPICAL ADHESION VALUES Stainless Steel: 180° Peel: 2.6 lb/in, Loop Tack: 2.00 lb/in² Glass: 180° Peel: 0.0 lb/in Polyethylene: 180° Peel: 2.2 lb/in Corrugated: 180° Peel: 1.1 lb/in Painted Metal: 180° Peel: 4.4 lb/in

REGULATORY APPROVAL RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: No UL:

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE's standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's plent); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

TECHNICOTE CORPORATE HEADQUARTERS 222 Mound Avenue Miamisburg, 0H 45342 800-358-4448 technicote.com