



## Item #3061

4 Mil Vinyl TC Flexible White / TS523 @ 1.40 Cwt. / 4.6 Mil Layflat L-3

### FACESTOCK

#### 4 Mil Vinyl TC Flexible White

A 4 mil flexible white vinyl with polymeric plasticizers, formulated to provide optimum performance with pressure sensitive adhesives. The top-coating provides outstanding adhesion to various printing inks.

**Type:** Film

**Caliper:** 4.0

**Opacity:** 90.0

**Brightness:** N/A

**Basis Weight:** N/A

**Tensile:** MD: 3900 lb/in, CD: 3800 lb/in

**Tear:** MD: 100 Grams, CD: 100 Grams

**Elongation:** MD: N/A, CD: N/A

#### REGULATORY APPROVAL

**RoHS:** Yes

**REACH:** Yes

**CPSIA:** Yes

**Prop 65:** Yes

**TPCH:** Yes

**Indirect Food:** Yes

**Direct Food:** No

**UL:**

### ADHESIVE

#### TS523 @ 1.40 Cwt.

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

**Adhesive Type:** Permanent Acrylic

**Shear:** 350 min.

**Minimum Application Temperature:** 35 F

**Service Temperature:** -65 F to 200 F

#### TYPICAL ADHESION VALUES

**Stainless Steel:** 180° Peel: 5.6 lb/in,

Loop Tack: 2.70 lb/in<sup>2</sup>

**Glass:** 180° Peel: 2.8 lb/in

**Polyethylene:** 180° Peel: 2.9 lb/in

**Corrugated:** 180° Peel: 4.0 lb/in

**Painted Metal:** 180° Peel: 4.6 lb/in

#### REGULATORY APPROVAL

**RoHS:** Yes

**REACH:** Yes

**CPSIA:** Yes

**Prop 65:** Yes

**TPCH:** Yes

**Indirect Food:** Yes

**Direct Food:** No

**UL:**

### RELEASE LINER

#### 4.6 Mil Layflat L-3

A clay coated kraft liner which has been silicone coated one side to give a controlled release. It is designed to withstand all diecutting, margin punching, perforating, fanfolding and refolding processes. It is an excellent layflat liner.

**Basis Weight:** 0 lb/ream

**Tensile:** MD: 51 lb/in, CD: 0

**Caliper:** 4.6 mil

**Tear:** MD: N/A, CD: N/A

#### REGULATORY APPROVAL

**RoHS:** Yes

**REACH:** Yes

**CPSIA:** Yes

**Prop 65:** Yes

**TPCH:** Yes

**Indirect Food:**

**Direct Food:**

**UL:**

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE'S standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

TECHNICOTE CORPORATE HEADQUARTERS 222 Mound Avenue Miamisburg, OH 45342 800-358-4448 [technicote.com](http://technicote.com)