

Item #84922

Techni-Prism Holographic Polyester Stardust / TR440 @ 1.00 Cwt.

FACESTOCK

Techni-Prism Holographic Polyester Stardust

This versatile top coating is compatible with solvent base, water base and UV curable inks, as well as silk screen, flexographic and offset/letterpress printing.

Type: Film Caliper: 2.00 Mil Opacity: N/A Brightness: N/A Basis Weight: N/A

Tensile: MD: 64 Lbs/in, CD: 42 Lbs/in **Tear:** MD: 1400 Grams, CD: N/A **Elongation:** MD: 300, CD: 110

REGULATORY APPROVAL

REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: No

RoHS: Yes

UL:

ADHESIVE

TR440 向 1.00 Cwt.

A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.

Adhesive Type: Removable Acrylic

Shear: 110 min.

Minimum Application Temperature: 40 F **Service Temperature:** 65- F to 150 F

TYPICAL ADHESION VALUES **Stainless Steel:** 180° Peel: 4.7 lb/in,

Loop Tack: 1.70 lb/in²
Glass: 180° Peel: 3.0 lb/in
Polyethylene: 180° Peel: 1.4 lb/in
Corrugated: 180° Peel: 3.2 lb/in
Painted Metal: 180° Peel: 4.5 lb/in

REGULATORY APPROVAL

RoHS: Yes REACH: Yes CPSIA: Yes Prop 65: Yes TPCH: Yes Indirect Food: Yes Direct Food: No

UL:

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE's standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.