

60# C1S Ultra White Semigloss FSC® / AP151 Opaque @ 1.30 Cwt. / 40#SCK L3

Facestock(60# C1S Ultra White Semigloss FSC®): A premium coated one side stock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face offers a 90% Brightness and an 88% opacity.

Type:	Paper	Basis Weight:	60#/Rm 25 x 38	<u>Regulatory Approval</u>	
Caliper:	3.2 mil	Tensile:	MD: 35 Lbs/in CD: 19 Lbs/in	RoHS:	Yes
Opacity:	88.5	Tear:	MD: 47 grams CD: 46 grams	REACH:	Yes
Brightness :	90	Elongation :	MD: N/A CD: N/A	CPSIA:	Yes
				Prop 65:	Yes
				TPCH:	Yes
				Indirect Food:	Yes
				Direct Food:	No
				UL:	

Adhesive(AP151 Opaque @ 1.30 Cwt.): An outstanding general purpose permanent opaque adhesive that has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting and stripping traits. Provides opacity for cover up applications.

Adhesive Type:	Permanent Latex	<u>Typical Adhesion Values</u>		<u>Regulatory Approval</u>	
Shear:	80 min.	Stainless Steel:		RoHS:	Yes
Minimum Application Temperature :	35 F	180° Peel:	7.3 lb/in	REACH:	Yes
		Loop Tack:	5.00 lb/in ²	CPSIA:	Yes
Service Temperature :	65- F to 220 F	Glass:	180° Peel: 5.7 lb/in	Prop 65:	Yes
		Polyethylene:	180° Peel: 6.5 lb/in	TPCH:	Yes
		Corrugated:	180° Peel: 7.3 lb/in	Indirect Food:	Yes
		Painted Metal:	180° Peel: 7.5 lb/in	Direct Food:	No
				UL:	

Release Liner(40#SCK L3): "Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing."

Basis Weight:	0 lb/ream	Caliper:	2.5 mil	<u>Regulatory Approval</u>	
Tensile:	MD: 34 lb/in	Tear:	MD: N/A	RoHS:	Yes
				REACH:	Yes
				CPSIA:	Yes
				Prop 65:	Yes
				TPCH:	Yes
				Indirect Food:	
				Direct Food:	
				UL:	

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE'S standards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

TECHNICOTE,INC.	222 MOUND AVENUE	MIAMISBURG, OH 45342	800-358-4448	FAX: 937-859-9096	www.technicote.com
-----------------	------------------	----------------------	--------------	-------------------	--