

60# Ultra White Semigloss C1S / TS583 @ 2.10 Cwt. / 40#SCK L-3

Facestock(60# Ultra White Semigloss C1S): A premium coated one side stock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face offers a 90% Brightness and an 88% opacity.

Type:	Paper	Basis Weight:	60 # Rm 25 x 38			Regulatory Approval
					RoHS:	Yes
Caliper:	3.20 Mil	Tensile:	MD: 35 Lbs/in	CD: 19 Lbs/in	REACH:	Yes
Opacity:	88.5	Tear:	MD: 47 Grams	CD: 46 Grams	CPSIA:	Yes
					Prop 65:	Yes
Brightness :	90	Elongation :	MD: N/A	CD: N/A	TPCH:	Yes
					Indirect Food:	Yes
					Direct Food:	No
					UL:	

Adhesive(TS583 @ 2.10 Cwt.): A specialty adhesive designed to adhere to hard to label surfaces with excellent ultimate adhesion when applied at temperatures as low as -20 F. Outstanding permanency at room temperatures. This adhesive has good plasticizer, UV & solvent resistance and high initial tack.

Adhesive Type:	Permanent	Typical Adhesion Values	Regulatory Approval	
	Acrylic	Stainless Steel:	RoHS:	Yes
Shear:	70 min.	180° Peel: 5.9 lb/in	Norio.	100
		Loop Tack: 3.20 lb/in²	REACH:	Yes
Minimum Application Temperature : Service Temperature :	20- F	Glass:	CPSIA:	Yes
		180° Peel: 4.2 lb/in		
		Polyethylene:	Prop 65:	Yes
	65- F to 160 F	180° Peel: 4.1 lb/in	TPCH:	Yes
	00- F 10 100 F	Corrugated:	Indirect Food:	Yes
		180° Peel: 4.9 lb/in	manect i ooa.	100
		Painted Metal:	Direct Food:	No
		180° Peel: 5.9 lb/in	UL:	

Release Liner(40#SCK L-3): "Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing."

Basis Weight:	0 lb/ream	Caliper:	2.5 mil	<u>Regu</u>	Regulatory Approval	
Tensile:	MD: 34 lb/in	Tear:	MD: N/A	RoHS:	Yes	
				REACH:	Yes	
				CPSIA:	Yes	
				Prop 65:	Yes	
				TPCH:	Yes	
				Indirect Food:		
				Direct Food:		
				UL:		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE's landards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

TECHNICOTE,INC.

222 MOUND AVENUE

MIAMISBURG, OH 45342

800-358-4448

FAX: 937-859-9096

www.technicote.com