

55# HiBright White Semigloss / AT333 @ 1.50 Cwt. / 40# SCK L-3 TU

Facestock(55# HiBright White Semigloss): A premium semigloss calendar coated one side stock with excellent ink receptivity and print characteristics. This stock offers an 88% brightness has an 87% opacity and a 70% gloss rating.

Type:	Paper	Basis Weight:	55			Regulatory Approval
					RoHS:	Yes
Caliper:	2.80 Mil	Tensile:	MD: 35 Lbs/in	CD: 16 Lbs/in	REACH:	Yes
Opacity:	87.0	Tear:	MD: 35 Grams MD: N/A	CD: 38 Grams CD: N/A	CPSIA:	Yes
					Prop 65:	Yes
Brightness :	88	Elongation :			TPCH:	Yes
					Indirect Food:	Yes
					Direct Food:	No
					UL:	

Adhesive(AT333 @ 1.50 Cwt.): An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Adhesive Type:	Permanent	Typical Adhesion Values	Regulatory Approval	
	Acrylic	Stainless Steel:	RoHS:	Yes
Shear:	60 min.	180° Peel: 4.7 lb/in		
		Loop Tack: 2.20 lb/in ²	REACH:	Yes
Minimum Application Temperature : Service Temperature :	20- F	Glass:	CPSIA:	Yes Yes
		180° Peel: 1.3 lb/in		
		Polyethylene:	Prop 65:	
	65- F to 160 F	180° Peel: 2.2 lb/in	TPCH:	Yes
	65- F t0 160 F	Corrugated:	la disent Feeds	Yes
		180° Peel: 3.9 lb/in	Indirect Food:	165
		Painted Metal:	Direct Food:	No
		180° Peel: 4.4 lb/in	UL:	

Release Liner(40# SCK L-3 TU): "Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. Technicote Ultimate silicone release coating provides consistent stripping at high converting speeds through a flat release profile. This paper has a smooth, caliper consistent surface and withstands all conventional processing operations."

Basis Weight: 40 lb/ream		Caliper: 2.5 mil		Regulatory Approval	
Tensile:	MD: 30 lb/in	Tear:	MD: N/A	RoHS:	Yes
				REACH:	Yes
				CPSIA:	Yes
				Prop 65:	Yes
				TPCH:	Yes
				Indirect Food:	
				Direct Food:	
				UL:	

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. TECHNICOTE will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages. TECHNICOTE warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), TECHNICOTE shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with TECHNICOTE's landards, correct such defects by suitable repair or replacement without charge at TECHNICOTE's plant or at the location of the products (at TECHNICOTE's election); provided, however, if TECHNICOTE determines that repair or replacement is not commercially practical, TECHNICOTE shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

TECHNICOTE,INC.

222 MOUND AVENUE

MIAMISBURG, OH 45342

800-358-4448

FAX: 937-859-9096

www.technicote.com